



Santa Maria

Drill Hole Results

2017 Drill Program

Commenced August 2017

Collar Table

Hole Name	Easting	Northting	Elev	Total Depth (m)	Azimuth	Hole Angle	Coordinate System
SM17-01	426451	2959994	2023	300	140	-75.0	UTM, Zone 13, NAD27
SM17-02	426422	2960096	2044	241.5	156	-69.0	UTM, Zone 13, NAD27
SM17-03	426501	2960019	2027	252	146	-74.5	UTM, Zone 13, NAD27
SM17-04	426443	2959993	2027	117.9	184	-56.0	UTM, Zone 13, NAD27
SM17-05	426405	2960038	2027	220	97	-68.9	UTM, Zone 13, NAD27
SM17-08	426496	2960018	2033	174	170	-75.0	UTM, Zone 13, NAD27

Highlighted Results

Hole No.	From (meters)	To (meters)	Drill Width (meters)	True Width (meters)	Ag (g/t)	Au (g/t)	Pb (%)	Zn (%)
SM17-01	49.2	51.7	2.5	1.06	604	0.84	0.19	0.13
SM17-02	225.7	226.5	0.8	0.4	255	0.77	1.56	1.49
SM17-03	216.2	221.2	5	2.5	431	0.29	0.49	0.99
SM17-04	60.7	65.7	5	2.5	217	0.49	0.56	0.23
SM17-05	194.1	194.9	0.7	0.4	164	0.4	0.61	3.76
SM17-08	141.6	148.5	6.9	2.36	310	0.77	0.4	0.91

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-01	49.15	50.12	0.458	231	0.18	0.13
SM17-01	50.12	50.75	2.04	659	0.38	0.21
SM17-01	50.75	51.66	0.282	934	0.06	0.08
SM17-01	51.66	52.52	0.103	54.8	0.04	0.09
SM17-01	52.52	53.52	0.115	33.8	0.02	0.06
SM17-01	53.52	53.83	0.187	55.7	0.01	0.07
SM17-01	53.83	54.95	0.066	62.7	0.04	0.03
SM17-01	54.95	55.7	0.037	23.4	0.01	0.02
SM17-01	55.7	56.85	0.085	27.3	0.03	0.06
SM17-01	56.85	58.03	0.06	23	0.01	0.04
SM17-01	58.03	59.5	0.057	22.3	0.01	0.04
SM17-01	59.5	60.34	0.054	27.9	0.01	0.04
SM17-01	60.34	61.37	0.04	29.9	0.01	0.03
SM17-01	61.37	62.35	0.051	24.9	0.01	0.03
SM17-01	62.35	63.35	0.069	25.9	0.02	0.06
SM17-01	63.35	64.1	0.053	28.7	0.01	0.03
SM17-01	64.1	65.16	0.108	30.1	0.02	0.05
SM17-01	65.16	66.3	0.056	19.4	0	0.01
SM17-01	66.3	67.58	0.063	32.2	0.01	0.03
SM17-01	67.58	68.5	0.063	55.2	0.01	0.02
SM17-01	68.5	69.85	0.086	34.6	0.01	0.03
SM17-01	69.85	71.73	0.052	16.9	0.01	0.02
SM17-01	71.73	72.1	0.044	29.8	0.01	0.03
SM17-01	72.1	73.1	0.04	27	0.01	0.04
SM17-01	73.1	73.83	<0.005	1.5	0	0.02
SM17-01	137.13	138.5	0.249	34.3	0.02	0.04
SM17-01	138.5	139.53	0.218	58.5	0.05	0.09
SM17-01	139.53	140.43	0.48	103	0.12	0.11
SM17-01	140.43	141.72	0.049	5.1	0.01	0.03
SM17-01	152.47	153.65	0.009	1.6	0	0.01
SM17-01	153.65	154	0.138	243	0	0.01
SM17-01	154	155.85	0.019	14	0	0.01
SM17-01	170	171.5	0.092	4.2	0	0
SM17-01	171.5	172.3	0.109	9.7	0.01	0.01
SM17-01	172.3	173.18	0.021	10.3	0.01	0.02
SM17-01	173.18	173.48	0.026	23.2	0.01	0.03
SM17-01	173.48	174.5	0.037	4.8	0.01	0.01
SM17-01	178.68	179.94	0.006	<0.5	0	0.01
SM17-01	179.94	181.56	<0.005	0.5	0	0.02

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-01	181.56	182.76	0.025	3	0	0.01
SM17-01	182.76	184.24	0.033	2.9	0	0.01
SM17-01	184.24	185.91	0.05	5.5	0	0.01
SM17-01	185.91	187.4	0.131	7.5	0	0.01
SM17-01	237.95	239.2	0.005	<0.5	0	0.01
SM17-01	239.2	240	0.01	0.6	0	0.01
SM17-01	240	241.25	<0.005	<0.5	0	0.01
SM17-01	245.17	246.35	0.04	<0.5	0	0.01
SM17-01	246.35	246.75	0.068	2.6	0	0.01
SM17-01	246.75	247.83	0.006	0.6	0	0.01
SM17-01	250.76	252.2	0.006	0.8	0	0.02
SM17-01	252.2	252.55	0.136	162	1.64	1.1
SM17-01	252.55	254.1	0.005	0.8	0	0.02
SM17-01	288.7	289.9	0.01	1	0	0.02
SM17-01	289.9	291	0.114	2.8	0	0.01
SM17-01	291	292.15	0.077	1.2	0	0.01

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-02	33.57	34.56	0.008	4.2	0.16	0.22
SM17-02	34.56	35.5	<0.005	5.3	0.15	0.29
SM17-02	35.5	36.29	0.006	5	0.07	0.23
SM17-02	55.1	56.22	0.008	3.8	0.01	0.03
SM17-02	56.22	56.9	0.012	5	0.02	0.08
SM17-02	56.9	58.1	0.027	4.3	0.02	0.04
SM17-02	63.2	64.5	0.009	3.7	0	0.05
SM17-02	64.5	66.15	0.021	8.1	0.03	0.09
SM17-02	66.15	66.55	0.009	3.1	0.05	0.09
SM17-02	66.55	68	0.007	1.8	0.02	0.08
SM17-02	98.3	99.55	0.014	0.9	0.02	0.05
SM17-02	99.55	100.35	0.282	15	0.03	0.08
SM17-02	100.35	101.46	0.006	0.7	0.03	0.07
SM17-02	104.85	105.74	0.008	<0.5	0.01	0.02
SM17-02	105.74	106.64	0.203	5.4	0.01	0.02
SM17-02	106.64	107.88	0.278	37.5	0.01	0.03
SM17-02	107.88	109.3	0.012	1.3	0.01	0.03
SM17-02	109.3	110.23	0.006	0.9	0.02	0.04
SM17-02	110.23	110.85	0.07	1.6	0.01	0.03

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-02	110.85	111.85	0.041	3.9	0.01	0.04
SM17-02	130.5	131.65	0.113	2.8	0.02	0.06
SM17-02	131.65	132.47	0.082	6.6	0.04	0.07
SM17-02	132.47	133.86	0.028	4.2	0.05	0.11
SM17-02	159.57	160.34	0.005	5.8	0.05	0.07
SM17-02	160.34	160.73	0.015	5.7	0.01	0.04
SM17-02	160.73	161.65	0.012	0.5	0.03	0.06
SM17-02	182.04	183.35	0.009	7.9	0.01	0.02
SM17-02	183.35	184.18	0.019	3.9	0.01	0.04
SM17-02	184.18	185.3	0.008	3.4	0.01	0.04
SM17-02	185.3	186.47	0.009	7.2	0.04	0.11
SM17-02	190.91	192.17	0.006	2.4	0.04	0.08
SM17-02	192.17	192.87	0.053	64	0.01	0.01
SM17-02	192.87	194.37	<0.005	0.8	0.02	0.04
SM17-02	200.37	200.9	0.113	4.4	0.03	0.06
SM17-02	200.9	201.83	0.013	2.1	0.01	0.02
SM17-02	201.83	203.55	0.018	4.2	0.02	0.03
SM17-02	203.55	204.84	0.012	2.5	0.01	0.01
SM17-02	204.84	205.5	0.016	6.3	0.01	0.03
SM17-02	205.5	205.8	0.024	4.2	0.01	0.05
SM17-02	205.8	206.67	0.008	1.2	0	0.01
SM17-02	214.84	215.95	0.005	0.8	0	0
SM17-02	215.95	217.42	0.034	4.3	0.01	0.05
SM17-02	217.42	217.92	0.144	15.1	0.01	0.36
SM17-02	217.92	219	0.036	7.1	0.01	0.03
SM17-02	219	220.45	0.037	12.7	0.01	0.01
SM17-02	220.45	222.19	0.09	9.3	0.01	0.02
SM17-02	222.19	223.5	0.014	3	0	0.02
SM17-02	223.5	224.73	0.033	5.2	0.01	0.04
SM17-02	224.73	225.7	0.07	10.3	0.01	0.02
SM17-02	225.7	226.46	0.774	255	1.56	1.49
SM17-02	226.46	227.37	0.253	10.5	0.01	0.02
SM17-02	227.37	228.32	0.206	17.8	0.01	0.02
SM17-02	228.32	229.62	0.041	5.2	0	0.02
SM17-02	229.62	230.65	0.132	15.3	0.01	0.02
SM17-02	230.65	231.6	0.088	8.9	0	0.02

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-03	4.8	7.71	0.122	55.3	0.01	0.05
SM17-03	7.71	9	0.043	65.2	0.01	0.03
SM17-03	28.35	33	0.033	2.6	0	0.02
SM17-03	33	36	0.136	16.1	0.01	0.03
SM17-03	36	41.85	0.049	36.3	0	0.03
SM17-03	48.4	49.45	0.008	1.5	0	0.01
SM17-03	49.45	49.75	0.13	38.9	0.01	0.04
SM17-03	49.75	51	0.005	3.7	0	0.01
SM17-03	63.7	64.8	0.022	59.2	0.01	0.03
SM17-03	64.8	65.9	0.452	259	0.03	0.05
SM17-03	65.9	66.7	0.167	77.7	0.04	0.08
SM17-03	66.7	67.9	0.007	1.5	0	0.01
SM17-03	81.3	82.4	<0.005	1.7	0	0.01
SM17-03	82.4	82.85	0.099	9.1	0.01	0.06
SM17-03	82.85	84	0.01	<0.5	0	0.01
SM17-03	108	109.2	0.013	3.1	0	0.02
SM17-03	109.2	110.7	0.075	63.9	0.03	0.05
SM17-03	110.7	111.25	0.146	26.2	0.02	0.05
SM17-03	111.25	112.4	0.018	9.7	0.01	0.04
SM17-03	112.4	112.8	0.012	13	0.01	0.02
SM17-03	112.8	114.4	0.022	7.8	0	0.02
SM17-03	114.4	115.3	0.023	7.3	0	0.01
SM17-03	115.3	116	0.029	13.3	0.01	0.02
SM17-03	116	116.8	0.03	12.6	0.01	0.03
SM17-03	116.8	118.1	0.013	13.5	0	0.02
SM17-03	118.1	119.4	0.006	15.4	0	0.01
SM17-03	119.4	121	0.006	12	0	0.01
SM17-03	121	122.55	0.017	8	0	0.01
SM17-03	122.55	123	0.108	15	0.02	0.03
SM17-03	123	124.55	0.031	8.9	0.01	0.03
SM17-03	124.55	126	0.02	7.3	0.01	0.04
SM17-03	182	183.6	0.012	14.2	0	0.02
SM17-03	183.6	183.95	0.119	49.6	0.05	0.07
SM17-03	183.95	184.45	0.058	9.4	0.03	0.06
SM17-03	184.45	185.8	0.028	10.4	0	0.07
SM17-03	194.2	195.3	0.047	21	0.01	0.06
SM17-03	195.3	196.55	0.174	34.4	0.03	0.07
SM17-03	196.55	197.2	0.042	32.1	0.01	0.05
SM17-03	197.2	198.2	0.075	21	0.02	0.05

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-03	198.2	198.8	0.105	35.2	0.03	0.05
SM17-03	198.8	199.9	0.311	42.1	0.03	0.04
SM17-03	199.9	201.55	0.396	39	0.06	0.07
SM17-03	201.55	202.15	0.054	44.6	0.02	0.14
SM17-03	202.15	203.35	0.008	4.3	0	0.03
SM17-03	203.35	204.6	0.01	1.8	0	0.01
SM17-03	204.6	206.1	0.012	2	0	0.01
SM17-03	206.1	207.6	0.006	1.8	0	0.01
SM17-03	207.6	209.1	<0.005	1.3	0	0.01
SM17-03	209.1	210.6	0.016	3.5	0	0.01
SM17-03	210.6	212.1	0.024	6.6	0.02	0.07
SM17-03	212.1	213.4	0.035	7.3	0.01	0.03
SM17-03	213.4	214	0.099	66.1	0.01	0.05
SM17-03	214	214.3	0.259	21.8	0.02	0.11
SM17-03	214.3	214.9	0.102	60.9	0.02	0.06
SM17-03	214.9	215.8	0.016	4.7	0.01	0.02
SM17-03	215.8	216.2	0.018	6	0.03	0.02
SM17-03	216.2	217.05	0.636	1625	1.26	2.72
SM17-03	217.05	217.95	0.119	75.3	0.15	0.25
SM17-03	217.95	218.8	0.064	25.4	0.08	0.13
SM17-03	218.8	220	0.213	176	0.5	0.91
SM17-03	220	221.2	0.402	329	0.43	0.92
SM17-03	221.2	222.25	0.216	54.5	0.1	0.1
SM17-03	222.25	223.45	0.252	64.8	0.05	0.07
SM17-03	223.45	224.05	0.104	8.8	0.01	0.03
SM17-03	224.05	225.2	0.028	18.4	0.02	0.12
SM17-03	225.2	226.7	<0.005	1.7	0	0.01

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-04	0	3.5	0.021	8.5	0.05	0.12
SM17-04	3.5	6	0.032	13.4	0.09	0.14
SM17-04	55.6	56.65	0.035	18.3	0.01	0.02
SM17-04	56.65	57.1	0.068	18.2	0.02	0.04
SM17-04	57.1	57.65	0.079	35.9	0.02	0.03
SM17-04	57.65	58.1	0.039	21.7	0.01	0.01
SM17-04	58.1	58.8	0.041	27.8	0.01	0.03

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-04	58.8	59.9	0.073	60.6	0.03	0.07
SM17-04	59.9	60.7	0.6	86.9	0.38	0.11
SM17-04	60.7	61.5	0.161	102	0.07	0.14
SM17-04	61.5	62	0.636	419	0.67	0.55
SM17-04	62	62.4	0.019	83.5	0.06	0.13
SM17-04	62.4	63.44	0.078	66	0.05	0.11
SM17-04	63.44	64.24	0.186	91.1	0.43	0.21
SM17-04	64.24	64.9	1.78	588	2.49	0.15
SM17-04	64.9	65.7	0.617	264	0.31	0.42
SM17-04	65.7	67	0.21	57.7	0.04	0.17
SM17-04	67	68.35	0.25	21.2	0.05	0.07
SM17-04	68.35	69.7	0.164	31.7	0.02	0.08
SM17-04	69.7	70.75	0.071	42.8	0.01	0.08
SM17-04	74.15	75.65	0.129	13.3	0.02	0.09
SM17-04	75.65	76.86	0.08	30.8	0.09	0.39
SM17-04	76.86	77.42	0.426	140	0.21	0.31
SM17-04	77.42	78.95	0.382	50	0.37	0.39
SM17-04	78.95	81.35	0.689	79.1	0.4	0.23
SM17-04	81.35	83.35	0.224	85.2	0.05	0.11
SM17-04	83.35	85.6	0.13	57	0.04	0.03
SM17-04	85.6	86.7	0.101	51.1	0.02	0.02
SM17-04	86.7	87.45	0.082	43.2	0.01	0.02
SM17-04	87.45	89	0.088	30.5	0.02	0.04
SM17-04	89	90.05	0.165	55.7	0.02	0.04
SM17-04	90.05	90.7	0.075	55.2	0.01	0.02
SM17-04	90.7	91.7	0.096	77.4	0.01	0.03
SM17-04	91.7	93	0.095	24	0.01	0.03
SM17-04	93	94.1	0.085	23.8	0.01	0.03
SM17-04	94.1	94.8	0.083	38.6	0.02	0.04
SM17-04	94.8	96.05	0.104	27.9	0.01	0.02
SM17-04	96.05	98.2	0.161	65.2	0.02	0.03
SM17-04	98.2	99.41	0.091	49.7	0.02	0.06
SM17-04	99.41	101	0.194	47.6	0.01	0.03
SM17-04	101	104.4	0.208	57.8	0.02	0.05
SM17-04	104.4	107	0.08	28.1	0.01	0.02
SM17-04	107	108.7	0.061	21.3	0.01	0.02
SM17-04	108.7	109.45	0.159	5.3	0.01	0.1
SM17-04	109.45	110.85	0.012	1.2	0	0.01

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-05	19.83	21	<0.005	0.9	0	0.01
SM17-05	21	22.97	0.006	2.7	0	0.02
SM17-05	22.97	24	0.01	2.6	0	0.01
SM17-05	24	27	0.036	2.8	0	0.01
SM17-05	27	28.6	<0.005	2.6	0	0.01
SM17-05	28.6	28.7	0.005	2.6	0	0.01
SM17-05	28.7	29.8	0.007	5	0	0.01
SM17-05	29.8	32.3	0.031	4.8	0	0.02
SM17-05	32.3	33	0.05	4.8	0	0.01
SM17-05	69.5	71.25	0.016	7.3	0.01	0.04
SM17-05	71.25	72.45	0.024	7.9	0.02	0.04
SM17-05	72.45	72.8	0.069	8.9	0.02	0.05
SM17-05	72.8	75	0.011	5	0	0.02
SM17-05	75	76.1	0.008	2.8	0	0.09
SM17-05	107.3	108.42	0.006	4.8	0.02	0.06
SM17-05	108.42	109.82	0.051	20	0.01	0.03
SM17-05	109.82	110.66	0.006	12.7	0.01	0.06
SM17-05	110.66	111.47	0.014	13.6	0.01	0.12
SM17-05	111.47	112.37	0.015	5.7	0.01	0.1
SM17-05	112.37	113.05	0.014	6.5	0.03	0.11
SM17-05	119.24	120.15	0.044	20.8	0.01	0.02
SM17-05	120.15	121.65	0.04	17	0.01	0.02
SM17-05	121.65	122.85	0.029	20.8	0.03	0.06
SM17-05	122.85	123.8	0.011	14.7	0.02	0.13
SM17-05	123.8	125.05	0.023	15.3	0.01	0.1
SM17-05	125.05	126	0.032	35.7	0.01	0.02
SM17-05	126	126.83	0.046	19.8	0.05	0.08
SM17-05	126.83	127.8	0.01	8.6	0.05	0.12
SM17-05	132	132.68	0.01	4.1	0.02	0.04
SM17-05	132.68	133.4	0.011	2.5	0.02	0.05
SM17-05	133.4	134.03	0.015	4.6	0.03	0.07
SM17-05	134.03	135.23	0.02	10.1	0.04	0.14
SM17-05	135.23	135.82	0.057	77.4	0.08	0.2
SM17-05	149.58	150.23	0.016	3.8	0.03	0.08
SM17-05	150.23	151.13	0.039	14.2	0.02	0.04
SM17-05	151.13	152.45	0.023	6.6	0.03	0.06
SM17-05	152.45	153	0.017	11.9	0.07	0.14
SM17-05	153	154.1	0.01	6.1	0.03	0.04
SM17-05	185.85	186.94	0.028	3	0.01	0.01

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-05	186.94	187.47	0.022	3.9	0	0.01
SM17-05	187.47	188.32	0.023	5.5	0.01	0.02
SM17-05	188.32	189.07	0.033	12.3	0.01	0.05
SM17-05	189.07	189.37	0.032	4.2	0.01	0.01
SM17-05	189.37	190.18	0.039	8.9	0.01	0.05
SM17-05	190.18	190.53	0.02	14.9	0.01	0.08
SM17-05	190.53	191.28	0.042	10.2	0.01	0.06
SM17-05	191.28	192	0.029	7.6	0.03	0.11
SM17-05	192	193	0.03	9.4	0.03	0.08
SM17-05	193	194.14	0.064	8.4	0.02	0.06
SM17-05	194.14	194.85	0.395	164	0.61	3.76
SM17-05	194.85	195.65	0.077	20.7	0.02	0.15
SM17-05	195.65	196.78	0.056	12.4	0	0.03
SM17-05	196.78	197.83	0.062	14.3	0.05	0.09
SM17-05	197.83	198.85	0.086	12.3	0.01	0.04
SM17-05	198.85	199.6	<0.005	0.6	0	0.01
SM17-05	199.6	201.26	0.007	1.8	0.01	0.01

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-08	11.69	13.29	0.034	29.1	0.01	0.1
SM17-08	13.29	14.36	0.234	79.8	0.04	0.07
SM17-08	14.36	15.23	0.138	54.6	0.02	0.08
SM17-08	15.23	16.26	0.047	25.7	0.01	0.04
SM17-08	16.26	17.1	0.123	53.7	0.01	0.04
SM17-08	17.1	17.56	0.034	35.6	0	0.03
SM17-08	17.56	18.1	0.064	32.1	0.01	0.04
SM17-08	18.1	19.08	0.105	34.8	0.02	0.05
SM17-08	19.08	20.25	0.029	13.7	0.01	0.05
SM17-08	23.42	25.06	0.075	7.4	0.01	0.04
SM17-08	25.06	25.86	0.11	9.4	0.01	0.1
SM17-08	25.86	27	0.056	8.6	0.01	0.07
SM17-08	27	28.4	0.055	8	0.01	0.05
SM17-08	28.4	28.6	0.106	7.9	0.01	0.05
SM17-08	28.6	29	0.031	10.3	0	0.03
SM17-08	32.3	33	0.187	8.7	0.02	0.05
SM17-08	33	33.21	0.02	1.9	0.01	0.05
SM17-08	33.21	33.96	0.009	1.3	0	0.03
SM17-08	42.2	42.71	0.015	8.3	0	0.03

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-08	42.71	43.13	0.055	7.7	0.02	0.07
SM17-08	43.13	43.96	0.016	5.3	0	0.04
SM17-08	46.08	47.34	0.016	6.5	0	0.04
SM17-08	47.34	48	0.026	12.7	0.01	0.03
SM17-08	48	49.2	0.067	8.9	0	0.03
SM17-08	49.2	49.96	0.087	10.3	0	0.03
SM17-08	49.96	51	0.052	5.2	0	0.03
SM17-08	63.3	64.3	0.01	1.4	0.01	0.02
SM17-08	64.3	64.9	0.006	2.6	0	0.01
SM17-08	64.9	65.63	<0.005	0.5	0	0.02
SM17-08	68.35	69	<0.005	<0.5	0	0.01
SM17-08	69	69.54	0.006	1.4	0.01	0.02
SM17-08	69.54	70.47	<0.005	0.8	0	0.02
SM17-08	70.47	71.72	<0.005	1.3	0	0.02
SM17-08	81.23	82.27	0.009	3.1	0	0.02
SM17-08	82.27	82.78	0.026	3.3	0.01	0.08
SM17-08	82.78	83.66	0.031	2.2	0	0.01
SM17-08	87.61	88.42	0.005	2.2	0	0.02
SM17-08	88.42	88.7	0.077	4.7	0	0.02
SM17-08	88.7	89.2	0.009	0.8	0	0.02
SM17-08	98.53	99.63	0.057	6	0	0.02
SM17-08	99.63	101.25	0.023	9.1	0	0.03
SM17-08	101.25	102	0.089	14	0	0.03
SM17-08	102	102.66	0.022	12.6	0	0.08
SM17-08	102.66	102.93	0.036	8.1	0.01	0.06
SM17-08	102.93	103.99	0.062	11.6	0	0.04
SM17-08	103.99	105.05	0.072	7.6	0	0.02
SM17-08	105.05	105.6	0.092	13.1	0	0.02
SM17-08	105.6	107.57	0.059	11.4	0	0.02
SM17-08	107.57	109.31	0.032	7	0	0.02
SM17-08	109.31	109.87	0.098	11.7	0.01	0.04
SM17-08	109.87	111.07	0.072	11.7	0	0.05
SM17-08	111.07	112.09	0.007	1.8	0	0.01
SM17-08	115.25	116.03	0.031	67	0.04	0.05
SM17-08	116.03	116.72	0.397	151	0.01	0.04
SM17-08	116.72	117.66	0.073	13.7	0.01	0.04
SM17-08	117.66	118.94	0.266	257	0.04	0.1
SM17-08	118.94	120	0.154	132	0.02	0.12

Hole_ID	From	To	Au ppm	Ag ppm	Pb %	Zn %
SM17-08	120	126	0.073	39.8	0.02	0.09
SM17-08	126	126.76	0.405	67.5	0.03	0.13
SM17-08	126.76	127.92	0.17	122	0.06	0.14
SM17-08	127.92	129.22	0.041	9.7	0.01	0.04
SM17-08	129.22	130.13	0.206	10.3	0.03	0.08
SM17-08	130.13	134.18	0.322	89.9	0.2	0.52
SM17-08	134.18	135.64	0.098	55.9	0.02	0.08
SM17-08	135.64	137.05	0.241	50.7	0.02	0.17
SM17-08	137.05	138.44	0.373	71.5	0.01	0.1
SM17-08	138.44	140.49	0.255	67.4	0.05	0.24
SM17-08	140.49	141.6	0.324	79.4	0.49	0.83
SM17-08	141.6	142.4	0.984	520	0.9	3.78
SM17-08	142.4	143.25	1.08	262	0.94	0.71
SM17-08	143.25	144.1	0.382	140	0.11	0.28
SM17-08	144.1	145.2	0.241	37.3	0.07	0.19
SM17-08	145.2	146.18	0.833	128	0.09	0.26
SM17-08	146.18	147.5	0.95	480	0.18	0.53
SM17-08	147.5	148.5	0.953	580	0.68	1.22
SM17-08	148.5	149.55	0.785	39.4	0.03	0.12
SM17-08	149.55	150.44	1.675	129	0.11	0.3
SM17-08	150.44	151.18	0.497	67.9	0.06	0.05
SM17-08	151.18	152.77	0.219	32.6	0.05	0.12
SM17-08	152.77	153	0.269	118	0.06	0.11
SM17-08	153	154.5	0.649	62.2	0.12	0.22
SM17-08	154.4	154.83	0.094	24.5	0.01	0.03
SM17-08	154.83	156.1	0.049	24.1	0.01	0.05
SM17-08	156.1	158.04	0.037	9.4	0.01	0.07
SM17-08	158.04	160.18	0.115	14.2	0.01	0.1
SM17-08	160.18	161.28	0.008	1.3	0	0.02
SM17-08	166.7	167.81	0.078	1.6	0	0.01
SM17-08	167.81	168.85	0.153	2.3	0	0.02
SM17-08	168.85	169.35	0.007	1.3	0.01	0.04